

Q8 Induco 30

Application

- The Q8 Induco grades are industrial oils for various purposes.
- The oils have been severely processed as a result of which discolouration even after a long time does not occur.

Benefits

- Good oxidation- and colour stability
- Light coloured
- Minimum evaporation losses by heating
- Low aromatic content
- Meets FDA 178.3620(c)

Properties	Method	Unit	Typical
Viscosity Grade			30
Absolute Density, 15 °C	D 4052	kg/m ³	873
Kinematic Viscosity, 40 °C	D 445	mm ² /s	30.0
Kinematic Viscosity, 50 °C	D 445	mm ² /s	20.2
Kinematic Viscosity, 100 °C	D 445	mm ² /s	5.15
V-G Constant	D 2140	-	0.821
Colour	D 1500	-	L0.5
Flash Point	D 92	°C	224
Pour Point	D 97	°C	-15
Carbon Residue, Rams.	D 524	% mass	0.07
Total Acid Number	D 974	mg KOH/g	<0.03
Refractive Index n ₂₀ /D	D 1218	-	1.481
Refractivity Intercept	D 2140	-	1.046
Aniline Point	D 611	°C	98
Ash	D 482	% mass	<0.01
Loss on heating, 163 °C, 3 h	D 6 / IP 45	% mass	0.1
U-V Absorptivity, 260 nm 1/g cm	D 2008	-	0.8
Hydrocarbon Characterization	D 2140		
Carbon Atoms in			
Aromatic Rings		%	5
Naphthenic Rings		%	31
Paraffinic Chains		%	64
Clay-Gel Absorption	D 2007		
Asphaltenes		% mass	<0.1
Polar Compounds		% mass	0.2
Aromatics		% mass	28
Saturates		% mass	71.8
DMSO extract	IP 346	%	<1

The figures above are not a specification. They are typical figures obtained within production tolerances.