



LITEN EP-2

GENERAL FEATURES:

LITEN® EP plastic greases are manufactured basing on refined mineral oil with the viscosity about 150 mm² at temperature 40 °C, lithium soaps of 12-hydroxystearic acid and a set of additives increasing their lubricating, antioxidative and anticorrosive properties.

APPLICATION:

LITEN® EP plastic greases are intended to lubricate rolling bearings exposed to high loads and for less loaded bearings which, however, are exposed to impact loads.
Grease range of application: from -20°C to +120°C even in contact with water.

Limit working temperatures may however be higher or lower depending on the bearing type and required lubrication periods.

- LITEN EP-0 is intended to lubricate bearings of central lubricated devices working in low temperatures (-20 to +120°C) and requiring forcing through of grease to long distances,
- Liten EP-1 is designed for lubrication of bearings of central lubricated devices working in moderate ambient temperatures and requiring forcing through of grease to long distances,
- Liten EP-2 is designed for lubrication of bearings of both central and individually lubricated devices working in high ambient temperatures and requiring forcing through of grease to short distances,
- Liten EP-3 is designed for lubrication of bearings of individually lubricated devices.

STANDARDS, APPROVALS. SPECIFICATION:

Liten® EP-2
DIN 51 502: KP2G-20
ISO 6743-9: BCHB-2



Physical and chemical properties:

PARAMETERS	UNIT	TYPICAL VALUES
NLGI class		2
Worked penetration at 25°C	mm/10	293
Penetration at - 20°C	mm/10	154
Dropping point	°C	210
Structural stability oil separation from grease (m/m)	%	0,6
Weld load	kG	250

NOTE:
Physicochemical parameters listed in the table are typical values. Real values are stated in quality control certificates attached to each product lot.

