

Q8 Induco 60

Application

- The Q8 Induco grades are industrial oils for various purposes.
- The oils have been severely processed as a result of which discolouration even after a long time does not occur.

Benefits

- Good oxidation- and colour stability
- Light coloured
- Minimum evaporation losses by heating
- Low aromatic content
- Meets FDA 178.3620(c)

Properties	Method	Unit	Typical
Viscosity Grade			60
Absolute Density, 15 °C	D 4052	kg/m ³	878
Kinematic Viscosity, 40 °C	D 445	mm ² /s	58.5
Kinematic Viscosity, 50 °C	D 445	mm ² /s	37.4
Kinematic Viscosity, 100 °C	D 445	mm ² /s	7.85
V-G Constant	D 2140	-	0.815
Colour	D 1500	-	0.5
Flash Point	D 92	°C	252
Pour Point	D 97	°C	-12
Carbon Residue, Rams.	D 524	% mass	0.07
Total Acid Number	D 974	mg KOH/g	<0.03
Refractive Index n ₂₀ /D	D 1218	-	1.482
Refractivity Intercept	D 2140	-	1.044
Aniline Point	D 611	°C	105
Ash	D 482	% mass	<0.01
Loss on heating, 163 °C, 3 h	D 6 / IP 45	% mass	0.01
U-V Absorptivity, 260 nm 1/g cm	D 2008	-	0.9
Hydrocarbon Characterization	D 2140		
Carbon Atoms in			
Aromatic Rings		%	4
Naphthenic Rings		%	29
Paraffinic Chains		%	67
Clay-Gel Absorption	D 2007		
Asphaltenes		% mass	<0.1
Polar Compounds		% mass	0.2
Aromatics		% mass	27.2
Saturates		% mass	72.6
DMSO extract	IP 346	%	<1

The figures above are not a specification. They are typical figures obtained within production tolerances.