

Q8 Puccini 17P

Application

- The Q8 Puccini process oils are mainly used in the rubber- and ink-industries.
- The oils have been severely processed as a result of which discolouration even after a long time does not occur.
- Application of the oils in compounding improves the low temperature properties of the rubber.

Benefits

- Good oxidation- and colour stability
- Light coloured
- Minimum evaporation losses by heating
- Low aromatic content

| Properties | Method | Unit | Typical |
|---------------------------------|-------------|----------|---------|
| Viscosity Grade | | | 17P |
| Absolute Density, 15 °C | D 4052 | kg/m³ | 857 |
| Kinematic Viscosity, 40 °C | D 445 | mm²/s | 17.0 |
| Kinematic Viscosity, 50 °C | D 445 | mm²/s | 12.1 |
| Kinematic Viscosity, 100 °C | D 445 | mm²/s | 3.67 |
| Viscosity Index | D 2270 | - | 99 |
| V-G Constant | D 2140 | - | 0.812 |
| Colour | D 1500 | - | L0.5 |
| Flash Point | D 92 | °C | 204 |
| Pour Point | D 97 | °C | -12 |
| Carbon Residue, Rams. | D 524 | % mass | 0.05 |
| Total Acid Number | D 974 | mg KOH/g | <0.03 |
| Refractive Index n20/D | D 1218 | - | 1.471 |
| Refractivity Intercept | D 2140 | - | 1.044 |
| Aniline Point | D 611 | °C | 96 |
| Ash | D 482 | % mass | <0.01 |
| Loss on heating, 163 °C, 3 h | D 6 / IP 45 | % mass | 1.1 |
| U-V Absorptivity, 260 nm 1/g cm | D 2008 | - | 0.6 |
| Hydrocarbon Characterization | D 2140 | | |
| Carbon Atoms in | | | |
| Aromatic Rings | | % | 4 |
| Naphthenic Rings | | % | 30 |
| Paraffinic Chains | | % | 66 |
| Clay-Gel Absorption | D 2007 | | |
| Asphaltenes | | % mass | <0.1 |
| Polar Compounds | | % mass | 0.1 |
| Aromatics | | % mass | 24.2 |
| Saturates | | % mass | 75.7 |
| DMSO extract | IP 346 | % mass | <1 |

 $The figures\ above\ are\ not\ a\ specification.\ They\ are\ typical\ figures\ obtained\ within\ production\ tolerances.$